




# Bull

**255**, price group 3

Bull presents a fusion of 100% recycled leather fibers on the backside and microfiber fabric on the front. This unique blend of materials makes it a top choice for customers seeking the perfect balance of comfort, durability, and aesthetic appeal. It results in remarkable sturdiness while maintaining a pleasant and soft-to-the-touch cover. Leather leftovers are ground by a shredder and, after a special process, flocked onto knitted microfiber. This unique leather fiber backing creates a special, comfortable, thick grip. The top layer is knitted microsuede with a leather print and embossing. It has also been finished with a treatment to prevent dampness and dirt. The combination of these elements produces a surface that is sumptuously smooth but resistant to daily wear and tear, promising lasting beauty for years to come.



Faceside: 96% Polyester, 4% Polyurethane  
Backside: 100% Leather



Martindale: 32.000




Lightfastness: 3-4

PRODUCT CHARACTERISTICS	
Product group	microsuede knitted
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	96% PES, 4%PU
Composition upside	100% LEATHER
Bonding	flocked leather
Statistic code	5907000090
Available colours	8

DURABILITY SPECIFICATIONS								
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	32.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-BO2:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	3-4		min. 4	min.5	C
	middle colours	CTL	grade	3-4		min. 4	min.5	C
	dark colours	CTL	grade	3-4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

PROCESSING SPECIFICATION								
Minimum workable width [cm]	± 138							
Roll length [m]	± 35							
Material weight [g/m]	± 672							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,088	825	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	73,7	54,1	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,1	13,9	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

CLEANING SPECIFICATIONS								
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a
			- Dirt and damp prevention treatment applied.					

All information is based on the data provided by the manufacturer.